

⑫ **EUROPEAN PATENT APPLICATION**

⑰ Application number: 89300036.4

⑱ Date of filing: 04.01.89

⑮ Int. Cl.⁴: **C 01 B 33/28**
B 01 J 29/28, C 07 C 5/41,
C 07 C 5/22

⑳ Priority: 04.01.88 GB 8800046

㉑ Date of publication of application:
12.07.89 Bulletin 89/28

㉒ Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

㉓ Applicant: **EXXON CHEMICAL PATENTS INC.**
1900 East Linden Avenue
Linden New Jersey 07036 (US)

㉔ Inventor: **Verduijn, Johannes Petrus**
Westersingel 34
3202 XL Spijkenisse (NL)

㉕ Representative: **Northover, Robert Frank et al**
Exxon Chemical Limited Exxon Chemical Technology
Centre PO Box 1
Abingdon Oxfordshire, OX13 6BB (GB)

㉖ **Zeolite L**

㉗ Binder-free shaped particles of caesium-containing zeolite L-potassium form (zeolite KL) are made by a process which comprises forming a mixture of shaped particles of silica-bound zeolite KL with an aqueous caesium-containing potassium aluminate solution and obtaining the desired binder-free shaped particles by crystallisation of the mixture. The shaped particles thus obtained can form part of a dehydrocyclisation and/or isomerisation catalyst.

Description

ZEOLITE L

This invention relates to the preparation of zeolite L and its use in catalysis, particularly for aromatisation.

Zeolite L has been known for some time as an adsorbent, and in US-A-3 216 789 is described as an

aluminosilicate of the formula:

$0.9 - 1.3 M_{2/n}O : Al_2O_3 : 5.2 - 6.9 SiO_2 : yH_2O$

(where M is an exchangeable cation of valency n and y if from 0 to 9) having a characteristic X-ray diffraction pattern. The preparation of zeolite L is described in US-A-3 216 789, EP-A-167755, EP-A-142355, EP-A-142347, EP-A-142349, EP-A-109199, PL-A-72149, US-A-3867512, and SU-548567.

EP-A-96479 describes and claims zeolite L having a characteristic morphology and size, which is particularly valuable for use as a catalyst base in hydrocarbon conversions such as aromatisation, and comprising crystallites in the form of cylinders with a mean diameter of at least 0.1 micron, preferably at least 0.5 micron.

EP 96479 describes a synthesis of zeolite L which is conducted so that the amount of the contaminant zeolite W, which is known to grow in such a system as a competitive phase, is minimised. A preferred synthesis

gel described in EP 96479 has the following mole ratios:

$2.62K_2O : Al_2O_3 : 10SiO_2 : 16OH_2O$

and it is discussed how this gel may be varied by changing the molar amount of one component within the following ranges:

K_2O :	2.4 - 3.0 moles
Al_2O_3 :	0.6 - 1.3 moles
SiO_2 :	8 - 12 moles
H_2O :	120 - 240 moles

EP-A-142353, EP-A-142354 and EP-A-185519 describe developments of this process for forming cylindrical zeolite L.

Zeolite L may be used as a catalyst base in aromatisation reactions. US 4 104 320 discloses dehydrocyclisation of aliphatic compounds in the presence of hydrogen using a catalyst comprising zeolite L and a group VIII metal. The particular zeolite disclosed in EP 96479 is remarkably effective in such aromatisation reactions being capable of forming catalysts which have extended lifetime. Such dehydrocyclisation and/or aromatisation reactions and catalysts for use in such reactions are also described in EP-A-107389, EP-A-184451, EP-A-142351, EP-A-145289, EP-A-184450, US-A-4614834, GB-A-2116450, GB-A-2114150, US-A-4458025, US-A-4456527, GB-A-2142648, GB-A-2106483, US-A-4443326, GB-A-2121427, GB-A-2153840, GB-A-2153384, US-A-4517306, US-A-4539304, US-A-4539305, US-A-4547472, GB-A-2166972, US-A-4579831, US-A-4608356 and EP-A-201856.

The product recovered from the usual methods used to prepare zeolite L is a fine sized crystalline material. Several of the uses as catalysts or molecular sieves require a product in a size range substantially larger than the size of the product recovered from the preparation processes of the prior art. To meet this demand, various binders are used in forming steps to prepare aggregates containing zeolite L as the principal ingredient such as pellets, extrudates, or tablets. These aggregates lose some of their activity per unit weight since the binder has a different and low activity and acts as a diluent of the molecular sieve activity and the conventionally-bound aggregates frequently do not have sufficient crushing strength, particularly when they contain the cylindrical zeolite L crystallites as described in EP-A-96479. In addition particles made using alumina as binder are susceptible to blocking of the zeolite pores, as a result of alumina migration. It is therefore highly desirable to develop a method of preparing binderless aggregates having a particle size suitable for catalyst or sieve systems and possessing good attrition resistance.

The prior art has developed processes of producing binderless sieve aggregates from silica and alumina starting materials such as silica-alumina catalysts and clay. Unfortunately the products produced by these processes, especially where clay is used as a starting material, generally have very poor attrition resistance and thus rapidly break during use into unsuitable powders which must be replaced.

US-A-3 650 687 describes processes for the preparation of binderless zeolite particles including zeolite L, in which an alumina silicate clay is slurried with an alkali silicate, spray dried to form particles of the desired finished size and then treated with an alkali and aged to convert the particles to zeolite. In an alternative, a hydrated clay is slurried and spray dried to form particles, then calcined and reacted with the other components necessary to form a zeolite. Thus zeolite is only formed after the final particles have been formed. Predictable formation of zeolite having optimum catalytic properties may be difficult under such circumstances.

Also spray drying can be used only to give small particles, typically of 100 to 400 microns, which are only suitable for fluidized beds whereas reactors usually need particle sizes of at least 0.8 mm, preferably at least 1.5 mm and typically 3 mm.

GB 1316311 describes binderless zeolite particles which may be of zeolite L, and which are formed by pelleting, crush and repelleting repeatedly to give products of the desired strength. This is a time-consuming procedure which is costly and can damage the zeolite crystals.

GB 2109359 describes preparation of zeolite 3A and 4A binderless particles in various processes in which kaolin clay and sodium hydroxide (in some cases with zeolite) are formed into beads and then reacted with further sodium hydroxide to form zeolite 4A (sodium form) which is exchanged to form zeolite 3A (potassium form). It is clearly stated that direct formation of a potassium zeolite is not possible in this process.

GB 2160517 describes the formation of so called preformed zeolite particles, which may be zeolite L particles prepared from a starting material, which may be a synthetic zeolite but must have a silica/alumina ratio lower than the product. The starting material is reacted with a silica material and an alkali to form the product. To form zeolite L either zeolite 3A, kaolin or a silica-alumina starting material is used. The products are necessarily more silica rich than the starting zeolite. This process has practical handling problems in treating particles with a silica containing material.

The prior art systems are either unsuitable for providing binderless particles of zeolite L having high catalytic or absorbent activity, or result in particles of inadequate strength to be suitable for handling in practical applications or are impractical for large scale operation.

It has been found that the potassium form of zeolite L hereinafter identified as zeolite KL shows enhanced properties as an aromatisation catalyst if it also contains some caesium. However attempts to replace some of the potassium ions by caesium ions in the preparation of zeolite KL have not been very successful in the past as the presence of caesium ions favours the formation of pollucite rather than zeolite L. We have now found a method of incorporating caesium in binder-free particles of the zeolite KL without any substantial formation of pollucite.

According to this invention binder-free shaped particles of caesium containing zeolite KL are prepared by a process comprising forming a mixture of shaped particles of silica-bound zeolite KL with an aqueous solution containing sources of caesium, potassium and aluminium and obtaining the binder-free caesium-containing shaped particles of zeolite KL by crystallisation of the mixture. In a modification of this process one can use the shaped particles of zeolite KL after they have been ground to finer particles of silica-bound zeolite KL. One then obtains a binder-free caesium-containing product which is also in ground form.

The binder-free particles obtained by the process of this invention have excellent physical strength without undesirable loss of catalytic performance and/or capacity.


When used herein in relation to the invention the terms "binderless" or "binder-free" refer to a plurality of individual zeolite L containing particles held together without the use of a significant amount of non-zeolitic binder. Preferably the particles contain less than 10 wt % (based on the weight of the total particles) of non-zeolitic binder. More preferably, the particles contain less than 5 wt % of non-zeolitic binders, and it is most preferable for the particles to be substantially free of non-zeolitic binder.

The shaped particles of zeolite KL may take various forms and are usually formed by extrusion to produce for example tablets or pellets.

The zeolite KL starting material is silica bound and this means that the binder is silica. The silica bound zeolite KL is usually derived from zeolite KL crystallites.

The zeolite L crystallites used as starting material may be prepared by any of the known procedures, such as those described in the patents identified hereinbefore as relating to zeolite L preparation. However, it is highly preferred that the zeolite L should be in a form having beneficial effects on the catalytic performance of the zeolite. The starting material may be a zeolite comprising crystallites in the form of cylinders with a mean diameter of at least 0.05 micron, preferably at least 0.1 micron, typically at least 0.5 micron, such as described in EP-A-96479).

The zeolite KL is preferably an aluminosilicate and will be described hereinafter in terms of being an aluminosilicate, though other elemental substitutions are possible, for example aluminium may be substituted by gallium, boron, iron and similar trivalent elements, and silicon may be substituted by elements such as germanium or phosphorus. The aluminosilicates preferably have a composition (expressed in terms of molar ratios of the constituent oxides in anhydrous form) of:



wherein x is from 4 to 7.5. The zeolite L preferably has high crystallinity as shown by a well defined X-ray diffraction pattern with sharp peaks.

The zeolite KL may be hydrated, typically with from 0 to 9 moles of water per mole of Al_2O_3 .

To make the silica bound zeolite KL, the zeolite KL crystals are thoroughly mixed with silica gel and preferably at a later stage in the mixing, methocel (hydroxypropyl methyl cellulose extrusion aid) is added and a very thick and smooth paste is obtained. The resulting paste usually can be collected and later extruded or otherwise shaped. The shaped particles eg extrudates, can then be dried to remove residual water and calcined in air.

The shaped particles of silica bound zeolite KL are mixed with an aqueous solution containing sources of caesium, potassium and aluminium, preferably a caesium-containing potassium aluminate solution. This solution should preferably have a mole ratio (expressed in terms of the oxides) of $K_2O/(K_2O + Cs_2O)$ of at

least 0.8.

The overall synthesis mixture expressed as moles of oxide except for caesium which is expressed as moles of CsX where X is halogen should preferably be:

2.50 to 3.20 K₂O/0.5 to 1.00 CsX/1.30 t 2.50 Al₂O₃/10 SiO₂/110 to 170 H₂O

5 How ever when CsOH.H₂O is used the overall synthesis mixture is preferably:

2.25 to 2.70 K₂O/0.025 to 0.50 Cs₂O/1.30 to 2.50 Al₂O₃/10 SiO₂/110 t 170 H₂O

The crystallisation is generally carried out in a sealed autoclave and thus at autogenous pr ssur . It is generally inconvenient, although possible to employ higher pressures. Lower pressure (and lower temperature) will require longer crystallisation times.

10 Crystallisation time is related to the crystallisation temperature. The crystallisation is preferably carried out at from 100°C to 200°C and at this temperature the crystallisation time may be from 15 to 96 hours, typically from 48 to 72 hours, with shorter times being possible with higher temperatures and/or higher alkalinity (K₂O/SiO₂). Lower temperatures may require much longer times and may also require adjustment of alkalinity to achieve good yield of the desired product, whereas times of less than 24 hours are possible when higher

15 temperatures are used.

After crystallisation the shaped particles should be washed with successive portions of water until the pH of the last wash water is between 9 and 10, e.g. about 9.5. The shaped particles should then be dried at a temperature of 130°C to 170°C, e.g. about 15 hours at 150°C.

20 X-ray diffraction (XRD) shows that the product of this invention consists of pure zeolite L and that the crystallinity increase versus the silica bound shaped particles of zeolite KL (the starting material) is up to 30%. This XRD-crystallinity increase is somewhat lower than in a similar synthesis wherein no caesium is used and this is an indication that the binder-free product contains caesium.

If the starting material is in the form of crushed particles the final product is also particulate. However this particulate product can be turned into shaped particles by use of conventional binder techniques, by the

25 binderless process disclosed in the specification of our patent application GB 8704365 or by the present process. It has been found that the binderless zeolite L particles prepared by the process of the invention are excellent catalyst bases and may be used in conjunction with one or more catalytically-active metals in a wide variety of catalytic reactions. The particular morphology of the crystals appears to result in a particular stable

30 base for catalytically active metals with a surprising resistance to metal catalyst deactivation. Also the particles have increased particle strength. In addition, they have displayed low acidity which makes them especially suited to catalytic applications where a low acid site strength is advantageous such as aromatisation. The catalytically-active metal(s) may be, for example, a Group VIII metal such as platinum, or tin or germanium as described in US-A-4104320, or a combination of platinum and rhenium as described in

35 GB-A-2004764 or BE-A-888365. In the latter case, the catalyst may for appropriate circumstances also incorporate halogen as described in US-A-4165276, silver as described in US-A-4295959 and US-A-4206040, cadmium as described in US-A-4295960 and US-A-4231897 or sulphur as described in GB-A-1600927.

A particularly advantageous catalyst composition incorporates from 0.1 to 6.0 wt.%, (based on the total weight of the composition), preferably from 0.1 to 1.5 wt.% platinum or palladium, since this gives excellent

40 results in aromatisation. From 0.4 to 1.2 wt.% platinum is particularly preferred. Accordingly the invention provides a catalyst comprising the binder-free zeolite obtained by the process of this invention and a catalytically-active metal. The zeolite L product of the process of this invention may be used in a process for the conversion of a hydrocarbon feed in which the feed is contacted with a catalyst as described above under appropriate

45 conditions to bring about the desired conversion. They may, for example, be useful in reactions involving aromatisation and/or dehydrocyclisation and/or isomerisation and/or dehydrogenation reaction. They are particularly useful in a process for the dehydrocyclisation and/or isomerisation of aliphatic hydrocarbons in which the hydrocarbons are contacted at a temperature of from 370 to 600°C, preferably 430 to 550°C, with a catalyst comprising zeolite L of the invention, and preferably incorporating at least one Group VIII metal having

50 dehydrogenating activity, so as to convert at least part of the aliphatic hydrocarbons into aromatic hydrocarbons.

The aliphatic hydrocarbons may be straight or branched chain acyclic hydrocarbons, and particularly paraffins such as hexane, although mixtures of hydrocarbons may also be used such as paraffin fractions containing a range of alkanes possibly with minor amounts of other hydrocarbons. Cycloaliphatic hydrocarbon

55 such as methylcyclopentane may also be used. In a preferred embodiment the feed to a process for preparing aromatic hydrocarbons and particularly benzene comprises hexanes. The temperature of the catalytic reaction may be from 370 to 600°C, preferably 430 to 550°C and preferably pressures in excess of atmospheric are used, for example up to 2000 KPa, more preferably 500 to 1000 KPa. Hydrogen is employed in the formation of aromatic hydrocarbons preferably with a hydrogen to feed ratio of less than 10.

60 The process is preferably otherwise carried out in the manner described in US 4104320, BE 888365, EP 0040119, EP 0142351, EP 0145289 or EP 0142352.

The invention is now described by the following Examples.

Example 1

A synthesis mixture was obtained by the mixing of two solutions - Solution A and Solution B - and the addition of extrudates of silica-bound zeolite KL. The weight of the reactant given in grams were as follows:

Solution A: Potassium aluminate solution:

KOH pellets (87.3% purity)	:	7.376
Al(OH) ₃ powder (purity 98.6%)	:	5.116
H ₂ O	:	16.46
Additional H ₂ O	:	5.89

The aluminium trioxide was dissolved by boiling and after cooling to ambient temperature the weight loss due to evaporation of water was corrected.

Solution B: CsCl

CsCl ($\geq 99\%$ purity)	:	1.679
H ₂ O	:	15.00
Additional H ₂ O	:	10.00

Extrudates of silica-bound zeolite KL : 40.00
(H₂O content 0.5 wt %
SiO₂ content 29.95 wt %)

The extrudates were prepared by the process according to Example 1b of our patent application GB 8704365.

Solution B was added to Solution A, the additional water being used to rinse the beaker containing Solution B. The combined Solution A/B was poured into a 300 ml stainless steel autoclave together with the 5.89 g additional water which was used to rinse the beaker containing Solution A/B. Next the extrudates of silica-bound zeolite KL were added to the contents of the autoclave.

The overall composition of the synthesis mixture (expressed as oxides) was:

2.89 K₂O/0.50 CsCl/1.63 Al₂O₃/10 SiO₂*/141 H₂O.

*Silica present as binder in the extrudate.

Crystallisation:

The autoclave was heated up over 6 hrs to 175°C and kept at this temperature for 65 hrs.

Washing and drying:

The extrudates were washed with 8 portions of water until the pH of the last washwater was 9.3. The total amount of water used was 3200 ml, the total washing time was 38 hrs. The extrudates were dried for 16 hrs at 150°C. The amount of extrudates recovered was 44.6 grams. The extrudates had an excellent physical strength having a crush strength of 3.12 lb/mm (1.42 kg/mm). This compares with crush strengths of conventional extrudates of about 1.07 lb/mm (0.49 kg/mm).

Properties of Extrudates:

Toluene adsorption capacity at 30°C and at p/p₀ = 0.25.

wt% toluene		
adsorbed	desorbed	micropore capacity
9.06	0.05	9.01

Chemical Analysis: Al 10.9 wt%, K 13.4 wt%
Cs 2.4 wt % and Si 26.7 wt%

X-ray diffraction showed that the product consisted of pure zeolite L, the crystallinity increase versus the silica-bound KL extrudates was 20%. The apparent XRD-crystallinity increase was somewhat lower than in similar synthesis in which no caesium is used (30% increase). This is an indication that the binder-free product contains caesium. Comparative diffractograms of the starting silica-bound extrudates and of the binder-free product are shown in Fig. 1a and 1b respectively.

SEM (scanning electron micrographs) showed that the amorphous silica binder was completely converted into zeolite L. Comparative 10000 * SEM micrographs of the starting silica-bound extrudate and the binder-free material are given in Figs. 2a, b and c in which Fig. 2a shows the starting silica-bound zeolite KL extrudate with an enlargement of 10000, Fig. 2b shows the binder-free zeolite KL product extrudate with an enlargement of 10000 and Fig. 2c is the same as Fig. 2b but with an enlargement of 20,000.

Example 2

In this Example binderfree KL extrudates in the presence of caesium were prepared. In the two syntheses the Cs concentration was increased from 0.50 Cs⁺/10 SiO₂ to 1.00 Cs⁺/10 SiO₂ and the Cs-source was CsCl in one case and Cs in the other case.

For the preparation of the first binderless KL extrudate (X) the synthesis mixtures (weight reactants in grams) were:

Solution A	KOH pellets (86.8%)	13.903	aluminate solution
	Al(OH) ₃ (98.6%)	9.592	
	H ₂ O	30.87	
	Additional water	12.28	
Solution B	CsCl powder (≥99%)	6.304	CsCl solution
	H ₂ O	27.98	
	Additional (rinsing) water	18.47	
	Silica bound extrudates	75.00	

After cooling to ambient temperature Solution A was poured into a 300 ml stainless steel autoclave. The beaker which contained the aluminate solution was rinsed with the additional water; this water was poured into the autoclave. The CsCl solution was poured into the autoclave together with the rinsing water. The contents of the autoclave were mixed. Next the silica bound extrudates were added to the contents of the autoclave. The composition (moles) of the synthesis mixture was:

2.87 K₂O/1.00 CsCl/1.62 Al₂O₃/10 SiO₂/141 H₂O

The mixture was then crystallised with a heat up rate of approx. 5 hours to 175°C and the mixture was held at 175°C for 65 hours.

Thereafter the extrudates were prewashed with 500ml water, followed by 9 further washings. The total amount of water was 3600 ml and total washing time 25 hours. The pH of the last wash water was 9.2. The extrudates were dried overnight at 150°C, and the weight of dry extrudates recovered was 87.1 grams. The weight increase of starting Si-bound extrudates was 16.1%.

XRD showed that the product was substantially pure zeolite L.
 For the preparation of the second binderless KL extrudate the Cs-source was CsOH.H₂O. In this synthesis the Cs-source also provides part of the alkalinity; therefore the potassium content was adjusted to give an alkalinity (K₂O + Cs₂O)/10 SiO₂ of 2.86.

The preparation synthesis mixture (weight reactants in grams):

A	KOH pellets (86.8%)	11.419	potassium-caesium	
	CsOH.H ₂ O ($\geq 99\%$)	6.286	aluminate solution	
	Al(OH) ₃ (98.6%)	9.596		
	H ₂ O	30.88		
	Additional (rinsing)	59.94		
	water			
	Silica bound	75.02		
	extrudates			

After cooling solution A was poured into a 300 ml stainless steel autoclave together with the rinsing water. After mixing the contents of the autoclave the Si-bound extrudates were added.

The composition (moles) of the synthesis mixture was:

2.36 K₂O/0.50 Cs₂O/1.62 Al₂O₃/10 SiO₂/142 H₂O (K₂O + Cs₂O)/10 SiO₂ = 2.86

The mixture was then crystallised with a heat up rate of approx. 4 hours to 175°C and the mixture was held at 175°C for 65 hours. Thereafter the extrudates were prewashed with 500ml of water, followed by further washings, the total amount of washwater was 3200 ml. The pH of the last wash water was 9.3. The extrudates were dried overnight at 150°C and the weight of the extrudates recovered was 87.2 grams. The weight increase of the starting Si-bound extrudates was 16.20%. XRD showed that the product was substantially pure zeolite L.

Claims

1. A process for preparing binder-free shaped particles of caesium-containing zeolite KL which comprises forming a mixture of shaped particles of silica bound zeolite KL with an aqueous solution containing sources of caesium, potassium and aluminium and obtaining the binder-free caesium-containing shaped particles of zeolite KL by crystallisation of the mixture.
2. A process according to claim 1 in which the shaped particles of silica-bound zeolite KL are derived from zeolite KL crystallites.
3. A process according to either of claims 1 and 2 wherein the aqueous solution containing sources of caesium, potassium and aluminium is a caesium-containing potassium aluminate solution.
4. A process according to any one of the preceding claims wherein the overall synthesis mixture expressed as moles of oxide except for caesium which is expressed as moles of CsX where X is halogen is:
 2.50 to 3.20 K₂O/0.05 to 1.00 CsX/1.30 to 2.50 Al₂O₃/10 SiO₂/110 to 170 H₂O, or where CsOH.H₂O is used
 2.25 - 2.70 K₂O/0.025 - 0.50 Cs₂O/1.30 - 2.50 Al₂O₃/10 SiO₂/110 - 170 H₂O
5. A process according to any one of the preceding claims wherein the mole ratio (expressed in terms of the oxide) of K₂O/K₂O + Cs₂O is at least 0.8.
6. A modification of the process according to any one of the preceding claims wherein the shaped particles of silica-bound zeolite KL are ground into finer particles of silica bound zeolite KL before being mixed with the aqueous solution containing sources of caesium, potassium and aluminium.
7. Binder-free particles of caesium-containing zeolite KL whenever prepared by the process according to any one of the preceding claims.
8. A catalyst comprising a catalytically active metal and the binder-free particles of caesium-containing zeolite KL according to claim 7.
9. A catalyst according to claim 8 wherein the metal is platinum or palladium in an amount of 0.1 to 6.0 weight % based on the total weight of the catalyst.

10. A process for the dehydrocyclisation and/or isomerisation of an aliphatic hydrocarbon in which the aliphatic hydrocarbon is contacted at a temperature of from 370°C to 600°C with the catalyst according to either of claims 8 and 9 so as to convert at least part of the aliphatic hydrocarbon into an aromatic hydrocarbon.

5

10

15

20

25

30

35

40

45


50


55

60

65

FIG. 1a








FIG. 2a




FIG. 2b



FIG. 2c

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 89300036.4

(51) Int. Cl.4: **C 01 B 33/28**

(22) Date of filing: 04.01.89

**B 01 J 29/28, C 07 C 5/41,
C 07 C 5/22**

(30) Priority: 04.01.88 GB 8800046

(43) Date of publication of application:
12.07.89 Bulletin 89/28

(84) Designated Contracting States:
AT BE CH DE ES FR GB GR IT LI LU NL SE

(88) Date of deferred publication of search report:
21.03.90 Bulletin 90/12

(71) Applicant: **EXXON CHEMICAL PATENTS INC.**
1900 East Linden Avenue
Linden New Jersey 07036 (US)

(72) Inventor: **Verduijn, Johannes Petrus**
Westersingel 34
3202 XL Spijkenisse (NL)

(74) Representative: **Northover, Robert Frank et al**
Exxon Chemical Limited Exxon Chemical Technology
Centre PO Box 1
Abingdon Oxfordshire, OX13 6BB (GB)

(54) **Zeolite L**

(57) Binder-free shaped particles of caesium-containing zeolite L-potassium form (zeolite KL) are made by a process which comprises forming a mixture of shaped particles of silica-bound zeolite KL with an aqueous caesium-containing potassium aluminate solution and obtaining the desired binder-free shaped particles by crystallisation of the mixture. The shaped particles thus obtained can form part of a dehydrocyclisation and/or isomerisation catalyst.

EP 0 323 892 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 30 0036

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
D,A	EP-A-0 096 479 (EXXON RESEARCH AND ENGINEERING CO.) * Claims 12,13 * ---	3	C 01 B 33/28 B 01 J 29/28 C 07 C 5/41 C 07 C 5/22
D,A	EP-A-0 142 355 (EXXON RESEARCH AND ENGINEERING CO.) * Claims 2,4 * ---		
D,A	EP-A-0 142 347 (EXXON RESEARCH AND ENGINEERING CO.) * Page 5, line 18 * ---		
D,A	EP-A-0 142 353 (EXXON RESEARCH AND ENGINEERING CO.) * Page 20, line 26 * ---		
A	DE-A-2 524 484 (W.R. GRACE & CO.) -----		
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 01 B 33/00
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 20-11-1989	Examiner BREBION J.CH.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EP 89 30 0036 (P0401)